



NORBOND®

OP45

Providing durable, long-lasting security

Finish Blocking Pad for Super Hydrophobic Lens Coating

Saint-Gobain NORBOND® OP45 is a new generation blocking pad designed specifically to bond to the latest generation of low surface energy super hydrophobic coatings. Based on the proven design of the highly successful OP Series, OP45 improves on this with the incorporation of a unique adhesive system engineered specifically to perform on the latest generation lens coatings. Good quick-stick, outstanding shear performance and easy release make this the ideal product for single-step edging.

NORBOND OP45 is specially designed to provide the following features:

- Microcellular polyurethane foam tape core provides good surface conformability and resists torque forces
- The adhesive for the lens surface is formulated to adhere to a wide range of the latest super hydrophobic coatings
- The adhesive system for the lens surface is identified to ensure error-free application
- Available in a wide range of die-cut shapes and sizes
- Suitable for a wide range of block types and edging equipment

Available Sizes

Standard thickness: 0.031 in.

Master roll size: 54 in. (1372 mm) width. Length varies with thickness.

Slit rolls also available.



Applications

- Blocking pads for optical lens edging

NORBOND® OP45 – Properties

(Formerly known as SecurEdge)

Performance tests are run using standard test procedures. The values presented are typical values and should not be used for specification purposes.

Property	Typical Value
Density: lb/ft ³ (kg/m ³)	33 (530)
Dynamic Shear Adhesion: 20 min. dwell Stainless steel overlap: psi (kPa)	90 (620)
90° Peel Adhesion: coated lens lbs/in. (N/cm)	1 (1.74)

Liners

A white paper liner is standard.

Important Instructions

- Because Saint-Gobain cannot anticipate or control every potential application, we strongly recommend testing of this product under individual application conditions prior to commercial use.
- Surfaces must be clean and free of oil, grease, moisture, dust and dirt. Isopropyl alcohol is good for cleaning the surface.
- Apply a uniform pressure of 15 psi (103 kPa) to promote good contact between the material to be bonded and the tape. The application temperature should be between 60°F and 125°F (16°C to 52°C). It is not recommended to apply these tapes at temperatures below 60°F (16°C), as the adhesive does not flow in this condition and can result in poor bonding.
- Recommended service temperature is between -40°F to 200°F (-40°C to 93°C).
- The adhesion between the substrate and the tape increases with time, typically reaching final bond strength in 72 hours. Heating the product above 105°F (40°C) will accelerate the adhesion process.

Shelf Life

12 months after the date of sale when stored in original packaging at temperatures up to 70°F (21°C) and 50% relative humidity.

NORBOND® OP45– Standard Roll Sizes

Product No.	Thickness in. (mm)	Length ft. (m)
OP45	.031 (.8)	216 (65)
OP45	.031 (.8)	432 (131)

NORBOND® is a registered trademark of Saint-Gobain Performance Plastics.



Saint-Gobain Performance Plastics

One Sealants Park
Granville, NY 12832

1-800-724-0883
Tel: (518) 642-2200
Fax: (518) 642-2793

foams@saint-gobain.com
www.foams.saint-gobain.com

The data and details in this document were correct and up-to-date at the time of printing and are intended to provide information on our products and their possible applications. It is the user's responsibility to obtain the latest version of the product data sheet. This data sheet is not a specification and does not assure specific product characteristics or make reference to the suitability of the product for a specific application. Because Saint-Gobain cannot anticipate or control every application, we strongly recommend testing of this product under individual application conditions. The application, use and conversion of this product are the user's responsibility.

Limited Warranty: For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse, or inability to use this product(s).

SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

NOTE: Saint-Gobain Performance Plastics Corporation does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.